

Technical data sheet

Aquafix S

8110

Texture paste for water-based coating systems, for use in industry and trade

PRODUCT DESCRIPTION

Product numbers

91201

General

Texture paste to create textured surfaces for use with colourless and pigmented water-based ADLER furniture paints and varnishes or Aquawood products for windows and exterior doors, Polycolor 2K SQ or ADLER Print-Protect. The product does not affect the surface quality of the paint or varnish system (chemical and mechanical resistance).

Application area



For hard-wearing surfaces with a textured effect, suitable for use in all interior finishing projects and in protected outdoor areas.

PROCESSING

Processing instructions



- Please shake the product before use.
- Carefully stir the Aquafix S (8110) into the unhardened and undiluted paint/varnish; then stir in the hardener and the required quantity of thinner.
- Mixed paints and stains must be processed as specified in the corresponding technical data sheet.
- Aquafix S (8110) will result in a noticeable reduction in the degree of gloss of the original paint/varnish – depending on the amount used.
- You can paint over coats of paint/varnish with Aquafix S (8110) (without intermediate sanding, within 24 hours); the degree of texture will, however, be somewhat reduced.
- Any change in the processing sequence, environmental conditions, non-observance of instructions or the use of products not listed may have an unfavourable effect on the result. Deviations lead to film and adhesion problems.

Quantity to be added



Max. 4 - 8% by weight of the paint/varnish.

Depending on the coating system, the following additional quantities are recommended:

Water-based ADLER furniture paints/varnishes, e.g. Bluefin Unistar (2965) Bluefin Pigmocryl NG G30 (3203) Bluefin Pigmocryl NG G40 (3204) Bluefin Pigmocryl NG G50 (3205)	
5 %	
Aquawood Protor-Finish D (5808) and Aquawood Protor-Finish L (5809) Aquawood Protect (5128) Aquawood Diamond-Top D (5090) and Aquawood Diamond-Top L (5196) Polycolor Top 2K (5082) ADLER Print-Protect UV+ SQ (5171)	up to a maximum of 8 %
Aquawood Covatop XT 20 (5020) Aquawood Covapro 20 (5023) Aquawood Covapro RS 20 (5045) or Aquawood Finatop 40 (5140) Aquawood Finapro 20 (5101)	up to a maximum of 4 %


Please refer to the corresponding technical data sheets of the products.

Drying times

(at 23 °C and 50 % rel. humidity)

The drying behaviour of the coating system is not affected by the addition of Aquafix S (8110).

Cleaning the working equipment



With water immediately after use.

To remove dried paint residues we recommend using Aqua-Cleaner (8029) (diluted 1:1 with water).

ORDERING INFORMATION

Size of trading unit

250 g, 650 g, 1 kg

Finer points

Aquafix S Grob (91201)

FURTHER DETAILS

Durability / storage



Min. 9 month(s) in the original sealed containers.

Make sure the product is protected against moisture, direct sunlight, frost and high temperatures (above 30 °C).

Safety information



The product is only suitable for the industrial and professional use.

Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet. The current version can be accessed on the Internet at www.adler-lacke.com.