

ADLER Glanzacryl

40701 ff



Product description

Water-thinnable acrylate-dispersion-based glossy coloured varnish for interior and exterior use with good all-round properties. Highly weather-resistant. Also appropriate for the varnishing of toys.

Fields of application

Finishing varnish for wood, steel, galvanised steel, aluminium and hard PVC.

ADLER Glanzacryl 40701 ff can also be used as a renovating coat on firmly adhering acrylic resin coatings.

Method of application

Painting (acrylic brush), rolling (short-hair roller), spraying

Priming

Wood 1 – 2 x using ADLER Acryl-Holzgrund 41001 (see technical data sheet)

Metal 1 – 2 x using ADLER Acryl-Unigrund 41191 (see technical data sheet)

Finishing coat

1 – 2 x using ADLER Glanzacryl 40701 ff, as required (intermediate drying time 5 - 6 hours)

Under extreme weather conditions (e.g. sheet metal roof) ADLER Ferro GSX 54120 ff is recommended

Thinning

Water, for spraying, approx. 10 - 15 %

Drying time (room temperature 20 °C)

Can be sanded or re-varnished after 5 - 6 hours

Application and object temperature

Not below + 10 °C

High humidity and/or low temperatures delay drying.

Tools

Clean with water immediately after use. Then thoroughly dry spray equipment in order to prevent rusting. Dried on paint residue can be removed using readily degradable ADLER Rote Krähe 95125 (paint remover).

Spreading rate (per application)

10 – 12 m²/l, according to state of surface

Container sizes

125 ml, 375 ml, 750 ml, 2,5 l

Storage

Cool, but frost-free

Storage life

3 years in sealed containers

Shades

Base W10	40701
Base W20	40702
Base W25	40740
Base W30	40703

12-10 (replaces 08-10) ZKL 4108

ADLER-Werk Lackfabrik, A-6130 Schwaz

Fon: 0043/5242/6922-190, Fax: 0043/5242/6922-309, Mail: info@adler-lacke.com

Continue

ADLER Glanzacryl 40701 ff

Base brown	40741
Base blue	40742
Base yellow	40743
Base green	40744
Base red	40745

RAL 9005 Jet black 40730

Further colour shades are mixable using the ADLER colour mixing system.

Safety information

Please refer to safety data sheet.

The usual protective measures should also be taken when using low-pollutant varnishes

PACHE SARL