

# Technical data sheet

## ADLER Holzentgrauer

96348

Effective cleaner and degreaser based on oxalic acid for weathered and grey wood for DIY and professional use

### PRODUCT DESCRIPTION

#### General


The slightly thixotropic product acts as an effective cleaner, degreaser and brightener. Restores the wood to its original colour (using bleach) and is biodegradable. Contamination, wood constituents and discolouration caused by metals can be gently removed. Intact coatings are not attacked.

#### Special properties and standards



- **French ordinance DEVL1104875A** regarding the marking of construction coating products for their emission of volatile pollutants: A+


#### Application areas



- Weathered and grey wood, e. g. garden furniture, terraces, timber cladding, balconies, etc.
- Preliminary treatment of tropical wood which is rich on wood extractives.


### PROCESSING

#### Instructions for use



- Please shake the product before use.
- Do not apply if temperatures are below 5 °C or higher than 30 °C and/or relative humidity > 80%.
- Do not process it under conditions of intense sunlight, rain, extremely high humidity, strong wind or pending frost.

### Application technique



Application method	Brushing
Yield per application (m <sup>2</sup> /l) <sup>1)</sup>	For degreasing: approx. 5 For cleaning: approx. 5 - 20
Dilution (thinning)	water
Addition of thinner in %	For degreasing: no dilution For cleaning: until 15% (maximum 1:5) depending on the impurity
<sup>1)</sup> yield without addition of thinner	

The shape, the properties and moisture of the substrate affect the consumption/yield.

Accurate values for consumption must be obtained by applying trial coats in advance.

### Cleaning the Working equipment



With water immediately after use.

## SUBSTRATE

### Preparation of the substrate

Remove weathered coatings; cover adjacent plants and sensitive surfaces which should not be cleaned or rinse immediately with water after use.

Pre-water absorbent substrates.

## COATING SYSTEM

### Product application

Deep application of ADLER Holzentgrauer with paint-brush or brush.

Impact time 10 - 20 minutes while keeping the surface always humid (for example with aerosol).

Wash afterwards with lots of water and with mechanical support (nylon- or coarse scrubbing brush; do not use metallic brushes). The mechanical support is necessary to remove also deep pore contamination.

In the case of strongly discoloured surfaces, we recommend using the product twice.

### Intermediate sanding



If necessary, the wood fibres can be smoothed with sandpaper or abrasive fleece before repainting.

### Subsequent coating

Intermediate drying: approx. 3 days with a relative wood moisture content of < 15 %, the surface can be recoated with the desired coating system such as Pullex Bodenöl.

---

## ORDERING INFORMATION

---

**Size of trading unit** 1.0 l; 2.5 l

---


**Color shades/degree of gloss** Leicht blau eingefärbt (slightly blue coloured) 96348

---

## FURTHER DETAILS

---

### Durability / Storage



At least 3 years in the original sealed containers.

Make sure the product is protected against moisture, direct sunlight, frost and high temperatures (above 30 °C).

Do not transfer the contents into metal containers.

---

### Safety-related information



Please pay attention to the associated safety data sheet. The current version can be accessed on the Internet at [www.adler-lacke.com](http://www.adler-lacke.com).

It is recommended to use safety gloves and safety glasses while processing.

---