

# Technical data sheet

**Pullex Aqua-IG**

**5357**

Water-based **protective wood impregnation treatment** for DIY and trade.

## PRODUCT DESCRIPTION

### General

Water-based, colourless, protective wood impregnation treatment with biocidal agents, for wood in outdoor settings. Uniform absorption, especially on softwoods.

### Special properties and standards



- **Approval as a wood preservative (PT8)**  
according to the Biocidal Products Directive of the EU.
- **Certificate of appreciation (10/91)**  
ARGE Holzschutzmittel (wood preservatives consortium), Association of the Austrian chemical industry
- **ÖNORM B 3802-2 or DIN 68800-3**  
The active substances used provide the protection required against blue stain (test conforming to EN 152-1) and wood-destroying fungi (test conforming to EN 113), as specified by ÖNORM B 3802-2 or DIN 68800-3, and also prevent insect infestation (test according to EN 46). Confirmed by an external test certificate.  
**Active substances: B, P, Iv, W**  
**Active agents:**  
9.0 g/kg (0.90 %) 3-Iod-2-propinylbutylcarbamat  
2.5 g/kg (0.25 %) Tebuconazol  
1.0 g/kg (0.10 %) Permethrin (ISO)  
0.5 g/kg (0.05 %) Polymeres Betain

### Application area



For non-dimensionally stable and limited dimensionally stable timber components for exterior use, such as e.g. wooden houses, timber cladding, canopies, profile boards, window shutters, balconies, gates.

For dimensionally stable timber components for exterior and interior use, such as e.g. wooden windows and front doors in the usage classes 2 and 3 without ground contact.

## PROCESSING

### Processing instructions



- Please stir the product before use.
- The temperature of the product and object, and the room temperature must be at least +10 C.
- The optimal conditions for use are between 15 - 25 °C with a relative atmospheric humidity between 40 - 80 %.
- Do not process it under conditions of intense sunlight, rain, extremely high humidity, strong wind or pending frost.
- The product is not weather-resistant without a topcoat!

1-1 IMC 5357 | 09/25 | replaces 1-0


ADLER-Werk Lackfabrik, A-6130 Schwaz

Fon: +43/5242/6922-190, Fax: +43/5242/6922-309, Mail: technical-support@adler-lacke.com

Our instructions are based on the current state of knowledge and are intended to advise the buyer/user to the best of our knowledge, but must be individually adapted to the areas of application and processing conditions. The buyer/user is responsible for deciding on the suitability and use of the supplied product, which is why we recommend that a sample be produced to check the suitability of the product. In all other respects, our General Terms and Conditions of Sale apply. All previous data sheets lose their validity with this edition. We reserve the right to make changes to container sizes, color shades and available gloss levels.

- The treated surfaces must be coated with a suitable topcoat to prevent the active substances from being washed out. This surface coating must be maintained continuously.
- Please read and take note of our **ARL 500 – Working guidelines for the coating of components that are not dimensionally stable or have limited dimensional stability – General section** and **ARL 056 – Working guidelines for the use of wood preservers**
- Please follow our **ARL 300 - Working guideline for coating dimensionally stable and limited dimensionally stable construction elements - General part** along with all standards and guidelines for window construction, **ARL 056 - Working guideline for the use of wood preservatives** and our **ARL 340 - Wood protection of dimensionally stable and limited dimensionally stable construction elements according to DIN 68800 part 1-3.**
- Any change in the processing sequence, environmental conditions, non-observance of instructions or the use of products not listed may have an unfavourable effect on the result. Deviations lead to film and adhesion problems as well as to impairments with regard to weathering and color stability.

### Application technique



	Flow coating	Immersion	Brushing
Applied quantity per application (ml/m <sup>2</sup> )	100 - 125		

#### Attention: Do not spray the product!

The product is ready to use.

An additional 40 % material consumption is to be expected on rough sawn timber.

The shape and surface condition of the workpiece as well as the type of application influence the actual consumption. Accurate values for consumption must be obtained by applying trial coats in advance.

### Drying times

(at 23 °C and 50 % rel. humidity)



Subsequent coating	approx. 4 hour(s)
--------------------	-------------------

The figures given above are reference values. The drying time depends on the type of substrate, coat thickness, temperature, air exchange and relative atmospheric humidity.

Lower temperatures and/or high level of atmospheric humidity can increase the drying time.

Avoid direct sunlight!

### Cleaning the working equipment



With water immediately after use.

## SUBSTRATE

### Type of substrate

Hardwoods and softwoods

### Substrate property

The substrate must be dry, clean, capable of holding the paint, free from separating substances such as grease, wax, silicone, resin etc. and free from wood dust, as well as tested for suitability for coating.

A prerequisite for ensuring long durability of the coating is to observe the basic principles of constructional wood preservation.

Please observe the additional documents:

- ÖNORM B 2230-1
- DIN 18363
- BFS data sheet no. 18.
- ÖNORM B 3430-1

---

**Wood moisture**

**Hardwoods:** 12 ± 2 %

**Softwoods:** 15 ± 2 %

---

**Substrate preparation**

For optimal durability we recommend to sand smooth wooden surfaces with grain size 80 – 120 in the direction of the fibre, clean thoroughly and remove wood extractives such as, for example, resins and resin pockets. Round off any sharp edges.

Clean resinous timbers containing drying retardant components with Nitro-Verdünner 8017 (8017).

Treat algae, green deposits or mould in outdoor areas with Aviva Fungisan (8308).

---

## COATING SYSTEM

---

**Impregnation**

1 x Pullex Aqua-IG (5357)

---

**Intermediate sanding**

Only necessary for windows and front doors.

Grit size 280

Remove sanding dust.

---

**Primer, intermediate coat and finishing coat**

Depending on application area: e.g.: Pullex Aqua-DSL (5338) or Pullex Aqua-Color (5325)

---

## ORDERING INFORMATION

---

**Size of trading unit**

750 ml, 2.5 l, 120 l

---

**Colour shades / Glosslevels**

**Standard colour(s):**  
Farblos (5357000200)

---

**Supplementary products**

Abbeizer Express (8313)  
Aviva Fungisan (8308)  
Nitro-Verdünner 8017 (8017)  
Pullex Aqua-Color (5325)  
Pullex Aqua-DSL (5338)

Please refer to the corresponding technical data sheets of the products.

---

## FURTHER DETAILS

---

**Durability / storage**

Min. 2 year(s) in the original sealed containers.

Make sure the product is protected against moisture, direct sunlight, frost and high temperatures (above 30 °C).

Close opened containers well and use up the content as soon as possible.

---

**Giscode**

HSW10

---

---

## Declaration of ingredients according to VdL-RL 01

alkyd resins / water / drying agents (siccatives) / anti-skin agent / wetting agent / surface additive / interface additives / glycol ether / biocides

Contains 3-iodo-2-propynyl butylcarbamate, permethrin (ISO) and 2-methyl-2H-isothiazol-3-one (MIT). May cause allergic reactions.

**Information for allergy sufferers under telephone no. +43 5242 6922-713.**

---

## Safety information



Use wood preservatives safely. Always read the label and observe the respective technical data sheets of the products before use.

Wood that has been freshly treated with Pullex Aqua-IG (5357) must be stored on an impermeable, hard surface after coating to prevent residues of the product from penetrating the ground or any bodies of water. Any leaking product must be collected for reuse or disposal.

Pullex Aqua-IG (5357) contains biocidal agents to protect against blue stain and wood-destroying fungi and helps to prevent insect infestations.

The product should therefore only be used when protection of the wood is prescribed or in specific cases when it is necessary.

Do not use indoors.

Must not be used for the treatment of rooms in which food or animal feed is obtained, produced, stored or sold.

Do not use for wood that will be made into apiaries or sauna complexes and do not use for wood that will be in permanent contact with soil and/or water.

Not suitable for wood that could come into direct contact with farm animals (e.g. in stables or fencing for pastures).

Keep cats away from treated surfaces as they are highly sensitive to permethrin.

Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet. The current version can be accessed on the Internet at [www.adler-lacke.com](http://www.adler-lacke.com).

---