

Technical data sheet

Vivido Varicolor

4117

Universal **matt primer and top coat** with priming effect for DIY and professional use

PRODUCT DESCRIPTION

General

An easy-to-apply, water-based matt primer and top coat for interior and exterior use with very good all-round properties. Universally applicable on various substrates. The low-odour product is block-resistant, aromatic-free, formaldehyde-free and resistant to yellowing. The product is characterised by excellent weather resistance and permanent elasticity, a very good stain-blocking effect against wood extractives, and good rust protection.

A finishing coat with rough glimmering texture can be achieved with Vivido Varicolor E20 (4139).

Glossy surfaces can be achieved by colourless overcoating with Vivido Varicolor Farblos Farblos, Glänzend (4161050252).

Special properties and standards



- **Colour fastness as per BFS data sheet no. 26**
Class A
Group 1-3 (depending on colour)
- **Heat-resistant up to approx. 100°C**
- **ÖNORM EN 71-3**
Confirmed by an external test certificate.
Safety of toys; migration of certain elements (free of heavy metals).
- **DIN 53160-1 and DIN 53160-2**
Perspiration and saliva-proof properties
- **declared product in baubook**
Criteria of the "Baubook Ökologisch ausschreiben" fulfilled
- **Cradle to Cradle Certified® Silver**
Cradle to Cradle Certified® is the global standard for products that are safe, circular and responsibly made.
- **French ordinance DEVL1104875A**
Confirmed by an external test certificate.
Marking of construction coating products for their emission of volatile pollutants: A+


3-0 IMC 4117 | 05/26 | replaces 2-0

ADLER-Werk Lackfabrik, A-6130 Schwaz

Fon: +43/5242/6922-190, Fax: +43/5242/6922-309, Mail: technical-support@adler-lacke.com

Our instructions are based on the current state of knowledge and are intended to advise the buyer/user to the best of our knowledge, but must be individually adapted to the areas of application and processing conditions. The buyer/user is responsible for deciding on the suitability and use of the supplied product, which is why we recommend that a sample be produced to check the suitability of the product. In all other respects, our General Terms and Conditions of Sale apply. All previous data sheets lose their validity with this edition. We reserve the right to make changes to container sizes, color shades and available gloss levels.

Application area



Efficient coating on wood, metal, rigid PVC and intact old coatings for exterior and interior use.

For dimensionally stable timber components for exterior and interior use, such as e.g. wooden windows and front doors.

Not suitable for coating floor and roof surfaces.

For non-dimensionally stable timber components in the outdoor area we recommend for example Pullex Color (4403) or Pullex Aqua-Color (5325).


For heavy weathering on metal, we recommend using Vivido Varicolor E20 (4139). Particularly suitable for wrought-iron works of art, such as lattices, fences or grave crosses.

For sheet metal roofs and steel constructions with extreme weathering we recommend Vivido Ferro GSX (4505). Coat horizontal sheet metal outdoors with Vivido Ferro-Color (4506) or Vivido Ferro GSX (4505).

We recommend ADLER Histo-Base (5497) / ADLER Histo-Protect (5097) for the restoration of oil paints and old, historic wooden windows and front doors.


PROCESSING

Processing instructions



- Please stir the product before use.
- The temperature of the product and object, and the room temperature must be at least +10 C.
- The optimal conditions for use are between 15 - 25 °C with a relative atmospheric humidity between 40 - 80 %.
- Resin flow cannot be avoided by the coating.
- Early exposure to water from rain or dew must be prevented!
- Use sealing profiles and masking tapes suitable for water-based paints.
- Sealants must be compatible with the coat and may only be applied once the paint has dried through. Sealing profiles with plasticizers tend to stick together in combination with paints.
- For application by brushing, an acrylic brush is recommended. Rolling is done using a short hair roller.
- Carefully cover and mask areas which are not to be coated.
- The color shade, compatibility and adhesion to the substrate must be checked by creating sample panels.
- Any change in the processing sequence, environmental conditions, non-observance of instructions or the use of products not listed may have an unfavourable effect on the result. Deviations lead to film and adhesion problems as well as to impairments with regard to weathering and color stability.

Application technique



	Cup gun	Brushing	Rolling
Spraying nozzle Ø (mm)	1,8 – 2,0	-	-
Spraying pressure (bar)	3 – 4	-	-
Diluent	Water		
Diluent amount added (%)	10 – 20	0 – 10	
Applied quantity per application (ml/m ²)	100 – 125		

The product is ready to use.

The shape and surface condition of the workpiece as well as the type of application influence the actual consumption. Accurate values for consumption must be obtained by applying trial coats in advance.

Drying times

Re-coatable at room temperature	approx. 6 hour(s)
---------------------------------	-------------------

(at 23 °C and 50 % rel. humidity)



Final hardness	approx. 7 day(s)
----------------	------------------

The figures given above are reference values. The drying time depends on the type of substrate, coat thickness, temperature, air exchange and relative atmospheric humidity.

Lower temperatures and/or high level of atmospheric humidity can increase the drying time.

Avoid direct sunlight!

Cleaning the working equipment



With water immediately after use.

To remove dried product residues we recommend using Clean Abbeizer-Express (8313).

SUBSTRATE

Type of substrate

Wood, wooden materials, metal as well as hard PVC

Substrate property

The substrate must be dry, clean, capable of holding the paint, free from separating substances such as grease, wax, silicone, resin etc. and free from wood dust, as well as tested for suitability for coating.

Please observe the additional documents:

- ÖNORM B 2230-1
- ÖNORM B 3430-1
- DIN 18363
- Current BFS information sheets

Wood moisture

Hardwoods: 12 ± 2 %

Softwoods: 15 ± 2 %

Substrate preparation

Wood and wood-based materials:

Break sharp edges and remove any wood extractives such as resins and resin galls.

Wood sanding Grit size 120 - 150

Iron and steel:

Remove rust down to bare metal. Thoroughly remove greasy or oily impurities using Clean Multi-Entfetter (7233).

Zinc, aluminium and other non-ferrous metals:

Sand until matt with abrasive fleece and Clean Multi-Entfetter (7233).

Hard PVC and coatable plastics:

Sand until matt with abrasive fleece and Clean Multi-Entfetter (7233).

Old coatings:

Sand intact old coatings with grit size 120 and clean.

Remove old coatings that cannot be recoated. The compatibility of the coating must be checked on intact old coatings.

COATING SYSTEM

General

The following coating systems are exemplary.

Impregnation

Wood and wood-based materials:

If necessary, impregnate outdoors once with Pullex Aqua-IG (5357) (applies to timbers of durability class 3-5 according to EN 350) to protect against blue stain, fungal decay and insect infestation.

Use wood preservatives safely. Always read the label and observe the respective technical data sheets of the products before use.

Please follow our **ARL 056 - Working guideline for the use of wood preservatives.**

Primer coat

Wood and wood-based materials:

For colored shades: 1 x Vivido Varicolor (4117)

White & pastel colours: 1 x Vivido Aqua-Primer Iso (4123) or Vivido Aqua-Primer Iso CT (4162) for optimum insulation

Iron and steel:

Indoors: 1 x Vivido Varicolor (4117)

Outdoors: Apply 1 saturated coat of Vivido Varicolor E20 (4139) blended (optionally Vivido Aqua-Primer Multi (4129) can be used)

Zinc, aluminium and other non-ferrous metals:

1 x Vivido Varicolor (4117)

Hard PVC and coatable plastics:

1 x Vivido Varicolor (4117)

Due to the large number of plastic materials, an adhesion test is recommended.

Old coatings:

No primer coating is required for intact old coatings, but the compatibility of the coating must be checked.

Damaged areas in not intact old coats must be pre-treated according to the respective substrate. Coating system like new paint.

Special cases:

For powder coatings we generally recommend priming with Vivido 2K-Epoxy-Primer Uni (5604). Make a sample and check adhesion. Please observe BFS data sheet no. 24.

Sand anodised aluminium and stainless steel very well until matt and prime within 60 minutes with Vivido 2K-Epoxy-Primer Uni (5604).

Intermediate sanding



If necessary, grind the primed surface with grit size 240 – 280.

Remove sanding dust.

Intermediate coat

1 x Vivido Varicolor (4117) (only necessary for iron and steel in outdoor areas)

Finishing coat

1 x Vivido Varicolor (4117)

MAINTENANCE

Care

The durability depends on several factors: these include particularly the type of weathering, constructive protection, mechanical stress and the choice of colour applied. To obtain long durability, regular inspection, maintenance and, if necessary, repair measures are necessary.

If required, remove dust and dirt from the still intact areas and paint 1 – 2 x using Vivido Varicolor (4117).

Maintenance

When renovating the outer surface of dimensionally stable wooden construction elements (windows and front doors), the coating on the inside must be checked and, if necessary, coated with the same system.

Please follow our **ARL 304 - Working guideline for coating dimensionally stable and limited dimensionally stable construction elements - Maintenance and repair.**

ORDERING INFORMATION

Size of trading unit

125 ml (standard colours only)
375 ml; 750 ml
2.5 l (for standard colours: RAL 6005 and RAL 9005 only)
10 l (white only, tintable)

Colour shades / Glosslevels

Color4You

Standard colour(s):

Weiß, tönbar (4117049100)
RAL1021 Rapsgeilb (4117001021)
RAL3020 Verkehrsrot (4117003020)
RAL5010 Enzianblau (4117005010)
RAL6005 Moosgrün (4117006005)
RAL7016 Anthrazitgrau (4117007016)
RAL7035 Lichtgrau (4117007035)
RAL8011 Nussbraun (4117008011)
RAL9001 Cremeweiß (4117009001)
RAL9005 Tiefschwarz (4117009005)
Farblos, Glänzend (4161050252)

Other colour shades can be obtained using the **ADLER colour mixing system Color4You.**

Base paint(s):

Vivido Varicolor Weiß, tönbar (4117049100)
Vivido Varicolor Basis W15 (4117000015)
Vivido Varicolor Basis W20 (4117000020)
Vivido Varicolor Basis W30 (4117000030)
Vivido Varicolor Basis Gelb (4117050087)
Vivido Varicolor Basis Rot (4117050088)
Vivido Varicolor E20 Basis E20 (4139071555)

In order to ensure uniformity of the colour shade, use only material with the same batch number on a given surface.

It is recommended to prepare a trial colour sample on the original substrate using the coating system selected in order to assess the final colour shade.

Depending on the system, brilliant and intensive color shades may have a lower covering power. Hence, it is recommended to apply a preliminary coat of a comparable, opaque and pastel colour shade based on W15.

Please consume blended products within 12 months.

Please observe our **ARL 800- Working guideline for working (including care and maintenance) with ADLER Mix, PUR Mix and Color4You dosing machines.**

Supplementary products

Vivido 2K-Epoxy-Primer Uni (5604)
Clean Abbeizer-Express (8313)
ADLER Histo-Base (5497)
ADLER Histo-Protect (5097)
Vivido Varicolor Farblos (4161)
Vivido Aqua-Primer Iso CT (4162)
Vivido Aqua-Primer Iso (4123)
Vivido Aqua-Primer Multi (4129)
Vivido Ferro-Color (4506)
Vivido Ferro GSX (4505)
Pullex Aqua-Color (5325)
Pullex Aqua-IG (5357)
Pullex Color (4403)

Please refer to the corresponding technical data sheets of the products.

FURTHER DETAILS

Durability / storage



Min. 3 year(s) in the original sealed containers.

Make sure the product is protected against moisture, direct sunlight, frost and high temperatures (above 30 °C).

Close opened containers well and use up the content as soon as possible.

Technical specifications

VOC content of the ready-to-use mixture: Limit value according to Directive 2004/42/EC for Vivido Varicolor (Cat A/d): 130 g/l.
Vivido Varicolor contains a maximum of 50 g/l VOC.

Giscode

BSW20

Declaration of ingredients according to VdL-RL 01

acrylic dispersions / inorganic white and coloured pigments / organic pigments / mineral agents / anti-corrosion pigments / water / glycol ether / rheology additives / interface additives / wetting agent / neutralising agents / in-can preservation agents

Contains 1,2-benzisothiazol-3(2H)-one, reaction mass of 5-chloro-2-methyl-2H-isothiazol-3-one and 2-methyl-2H-isothiazol-3-one (3:1). May cause allergic reactions.

Information for allergy sufferers available at Tel. +43 5242 6922-713.

Safety information



The usual protective measures must also be observed when processing low-pollutant products.

During sanding use P2 / P3 dust filter. Do not inhale spray mist. Use combination filter A2 / P2 and safety goggles.

If medical advice is needed, have the packaging or label ready.

If the product comes into contact with your eyes, rinse immediately with water.

It should be kept out of reach of children.

Ensure good ventilation during application and drying.

During work, do not eat, drink or smoke.

Do not allow to enter drains, water courses or soil.

Only dispose of empty containers for recycling, liquid material residues can be disposed of as water-based paint waste, dried material residues as hardened paint or as household waste.

Further information on the subject of safety during transport, storage and handling as well as disposal can be found in the relevant safety data sheet. The current version can be accessed on the Internet at www.adler-lacke.com.